

FEATURES GUIDE

CLASSIC COLLECTION





DATA SHEET CLASSIC COLLECTION

Pelle bovina pieno fiore anilina di spessore finito 0,9 – 1,1 mm.
Superficie media pelle circa 4,8 – 5,0 m². Concia al cromo.
Tintura passante, rifinitura con olii - cere naturali e resine. Articolo con mano ferma, tatto ceroso ed aspetto lucido con effetto bicolore.

Full grain bovine of European origin, finished thickness 0.9 – 1.1 mm.
Average leather surface approx. 4.8 – 5.0 sqm. Chrome tannage.
Aniline dyed, finishing with oils - natural waxes and resins. Article with a firm, waxy feel and shiny appearance with a light two-tones effect.

Europäisches Rindsleder, Typ Anilinleder.
Stärke 0,9 – 1,1 mm. Durchschnittliche Hautgröße ca. 4,8 – 5,0 qm.
Oberfläche mit Ölen, natürlichen Wachsen und Harzen behandelt. Glänzende Optik sowie zweifarbiger Effekt.

Vachette origine Européenne, pleine fleur aniline, grains naturels.
Épaisseur: 0,9 – 1,1 mm. Surface Moyenne: 4,8 – 5,0 m².
Le séchage sous vide, la finition bicolore à l'huile e aniline avec un effet légèrement pull-up font de cet article un choix haut de gamme.
Touché ciré, aspect lisse et semi brillant. Cette couleur naturelle est obtenue par la transparence d'une légère finition appliquée sur la peau.

Analisi Test Analysen Essai	Metodo di prova Test Method Prüfverfahren Test Méthode	Unità di misura Measurement Unit Maßeinheit Unité de Mesure	Garantito Guaranteed Garantiert Assuré
Resistenza allo sfregamento tipo Veslic Colour fastness to and fro rubbing Abriebfestigkeit nach Veslic Résistance aux frottements (Veslic)	UNI EN ISO 11640	ISO 105 A03	> = 4 > = 4
Sudore Alcalino Sweat Alkaline Solution Alkalischer Schweiß Sueur Alcaline ISO 11641 pH 8	Sudore - Sweat - Schweiß - Sueur 20 c		> = 4
Resistenza alla luce, lampada ad arco di Xeno Colour fastness to artificial light Xenon arc UV-Beständigkeit, Xenon ARC-Labortest Résistance à la lumière, lampe Xénon	UNI EN ISO 105 B02	Scala dei Blu Blue Scale Blauskala Echelle des bleus	> = 2
Resistenza alla flessione Flexing endurance Biegefestigkeit Résistance à la flexion	ISO 5402	Cicli Cycles Zyklen Cycles	> 50.000
Determinazione del pH Determination of pH Bestimmung vom pH-Wert Evaluation du pH	ISO 4045	pH	> = 3,5
Indice di differenza (Solo per pH < 4) Difference figure (only for pH < 4) Differenzindex (nur für pH < 4) Indice de différence (seulement pour le pH < 4)			< = 0,7
Resistenza allo Strappo Pantalone Tear strength - Single edge tear Reißfestigkeit Hose Résistance au déchirement	ISO 3377-1	N	> = 20



LEATHER CARE INSTRUCTIONS CLASSIC COLLECTION

Protect against excessive sunlight, dryness and heat:

Sunlight will fade and dry out the leather.

Dryness will cause the leather to crack.

Heat will dry out the leather and cause further damage.

How to remove spots and stains:

Blot excess liquid up as quickly as possible with a clean microfibre cloth.

If necessary, use clean lukewarm water only and let dry naturally. Do not dry with hair dryer, etc.

If water is used, clean the entire area where spot occurred seat cushion, arm, etc.

DO NOT RUB.

How to remove butter, oil or grease:

Wipe excess butter, oil or grease off the leather with a clean microfibre cloth. Then leave it alone as the spot should dissipate as much as possible into the leather in a short period of time.

Do not apply water or try to wash the butter, oil or grease spot.

How to remove chewing gum:

Place ice cubes in a plastic bag and apply on the chewing gum. Wait several minutes, lift the ice bag and remove the chewing gum.

General Care

DO NOT USE CHEMICALS, SADDLE SOAP, CLEANING SOLVENTS, FURNITURE POLISH, OILS, VARNISH, ABRASIVE CLEANERS, SOAP OR AMMONIA WATER.


For further informations, contact AMS.

These are recommended or suggested methods of cleaning. The manufacturer is not responsible for damage incurred while cleaning. Always try the cleaning method in a hidden area first to see results.



PRODUCT FEATURES AND IMPERFECTIONS THAT MAY OCCUR


NECK CREASES



Neck creases are a normal phenomenon and do not affect the value of the leather. Neck wrinkles naturally occur in a hide as a result of the neck stretching and contracting.



NATURAL GRAIN



Full grain bovine of European origin, aniline dyed, finishing with oils.




Note: Although every effort is made to ensure that the leather ordered match the colours from our catalogues, slight variations may occur from batch. We advise to always make a sample request from the colour you may need.



PRODUCT FEATURES AND IMPERFECTIONS THAT MAY OCCUR

MEASURES



The average size of a hide in Classic collection is 5.00 M2.

A - 1.70 MT (+-)

B - 2.15 MT (+-)

C - 1.95 MT (+-)

Note: Although every effort is made to ensure that the leather ordered match the colours from our catalogues, slight variations may occur from batch. We advise to always make an sample request from the colour you may need.