

FEATURES  
GUIDE

NABUK  
COLLECTION

A



# DATA SHEET NABUK COLLECTION

- Bovine hides
- Origin: European
- Average size: 4.80/5.00 m<sup>2</sup>
- Thickness: 1.1-1.3 mm
- Tanning: Mineral

- Peaux des Bovins
- Origine: Européen
- Superficie moyenne: 4.80/5.00 m<sup>2</sup>
- Epaisseur: 1.1-1.3 mm
- Bronzage : minéral

- Cueros de Bovinos
- Origen: Europeo
- Tamaño promedio: 4.80/5.00 m<sup>2</sup>
- Espesor: 1.1-1.3 mm
- Curtido: mineral

## • Available in 21 colours

Natural grain aniline bovine of European origin, with flat look and typical velvet feel  
Pure aniline with waterproof treatment finished using special anilines and greases  
Writing effect, with a soft and warm feel

## • Disponible en 21 couleurs

Aniline de grain naturelle bovine d'origine Europée, avec un aspect plat une sensation typique de vêtements  
Aniline pure avec traitement imperméable fini avec anilines et graisses spéciales  
Effect d'écriture, avec une sensation douce et chaude

## • Disponible en 21 colores

Aniline de grana natural bovina de origen europeo, con aspecto plano y sensación típica de terciopelo  
Anilina pura con tratamiento impermeable acabado con anilinas especiales y grasas  
Efecto de escritura, con una sensación suave y cálida

Differences of colour from lot to lot are to be considered normal.

Differences de couleur d'a lot a doivent être considérées comme normaux.

Diferencias de color de lote a lote son para considerarse normal.

## APPLICATION UPHOLSTERY

## APPLICATION TAPICERIE D'AMEUBLEMENT

## APLICACION TAPICERIA

## PHYSICAL AND COLOUR FASTNESS CHARACTERISTICS

## PHYSIQUE ET LES CARACTERISTIQUES DE SOLIDITE DES COULEURS

## CARACTERÍSTICAS FÍSICAS Y DE SOLIDEZ DEL COLOR

Dry rubbing Frottement sec Frotamiento seco	100 Cycles   Cycles   Ciclos	UNI EN ISO 11640	>4 Grey scale Échelle de gris Escala de Grises
Wet rubbing Mouiller à friction Frotamiento mojado	25 Cycles   Cycles   Ciclos	UNI EN ISO 11640	>4 Grey scale Échelle de gris Escala de Grises
Heat resistant Résistante à la chaleur Resistente al calor		UNI EN ISO 17228	>3 Grey scale Échelle de gris Escala de Grises
Colour fastness to light Solidité des teintures à la lumière Solidez del color a la luz		UNI EN ISO 105-B02	> 3 Blue scale Échelle de bleu Escala de Azul
Fire Resistance Résistance au feu Resistencia al fuego	UNI EN 1021/1 UNI EN 1021/2		BS5852 Source   Fuente 0.1 IMO FTP8 Res. A652 California TB117



# LEATHER CARE INSTRUCTIONS CLASSIC COLLECTION

## **Protect against excessive sunlight, dryness and heat:**

Sunlight will fade and dry out the leather.

Dryness will cause the leather to crack.

Heat will dry out the leather and cause further damage.

## **How to remove spots and stains:**

Blot excess liquid up as quickly as possible with a clean microfibre cloth.

If necessary, use clean lukewarm water only and let dry naturally. Do not dry with hair dryer, etc.

If water is used, clean the entire area where spot occurred seat cushion, arm, etc.

## **DO NOT RUB.**

## **How to remove butter, oil or grease:**

Wipe excess butter, oil or grease off the leather with a clean microfibre cloth. Then leave it alone as the spot should dissipate as much as possible into the leather in a short period of time.

**Do not apply** water or try to wash the butter, oil or grease spot.

## **How to remove chewing gum:**

Place ice cubes in a plastic bag and apply on the chewing gum. Wait several minutes, lift the ice bag and remove the chewing gum.

## **General Care**

**DO NOT USE CHEMICALS, SADDLE SOAP, CLEANING SOLVENTS, FURNITURE POLISH, OILS, VARNISH, ABRASIVE CLEANNERS, SOAP OR AMMONIA WATER.**


## **For futher informations, contact AMS.**

These are recommended or suggested methods of cleaning. The manufacturer is not responsible for damage incurred while cleaning. Always try the cleaning method in a hidden area first to see results.



## PRODUCT FEATURES AND IMPERFECTIONS THAT MAY OCCUR


### NECK CREASES




Neck creases are a normal phenomenon and do not affect the value of the leather. Neck wrinkles naturally occur in a hide as a result of the neck stretching and contracting.



### NATURAL GRAIN



Natural grain aniline bovine of European origin, with a flat look and typical velvet feel.




Note: Although every effort is made to ensure that the leather ordered match the colours from our catalogues, slight variations may occur from batch. We advise to always make a sample request from the colour you may need.



## PRODUCT FEATURES AND IMPERFECTIONS THAT MAY OCCUR

### MEASURES



The average size of a hide in Nabuk collection is 5.00 M2.

A - 1.70 MT (+-)

B - 2.15 MT (+-)

C - 1.95 MT (+-)

Note: Although every effort is made to ensure that the leather ordered match the colours from our catalogues, slight variations may occur from batch. We advise to always make an sample request from the colour you may need.