

FEATURES
GUIDE
PACIFIC
COLLECTION

A



DATA SHEET PACIFIC COLLECTION

- Bovine hides
- Origin: European
- Average size: 4,60/5,00 m²
- Thickness: 1.0 - 1.1 mm
- Natural half Grain
- Semi Aniline
- Available in 21 colours

Bovine of European origin, lightly buffed natural grain

Chrome tannage

Through dyed; finishing with resin and pigments Article with a pigmented and protective coat With a soft, waxy feel and semi-matt appearance

- Peaux des Bovins
- Origine: Européen
- Superficie moyenne: 4.60/5.00 m²
- Epaisseur: 1.0 - 1.1 mm
- Grain de moitié Naturel
- Aniline Semi
- Disponible en 21 couleurs

Vachette rectifié ou corrigé et grains naturels d'origine Européenne

Tannage Chrome

Teint dans la masse. Cet article de haute qualité a une main très souple sur toute la superficie et un touché ciré. Aspect: Semi opaque

- Cueros de Bovinos
- Origen: Europeo
- Tamaño promedio: 4.60/5.00 m²
- Espesor: 1.0 - 1.1 mm
- Grano Médio Natural
- Semi Anilina
- Disponible en 21 colores

Bovino de origen Europeo, ligeramente pulida natural grano

Curtido de Cromo

Teñido; Acabado con resinas y pigmentos

Artículo con capa pigmentada y protectora, con un aspecto mate y semi suave sensación

Differences of colour from lot to lot are to be considered normal.

Differences de couleur d'a lot a doivent être considérées comme normaux.

Diferencias de color de lote a lote son para considerarse normal.

APPLICATION
UPHOLSTERY

APPLICATION
TAPICERIE D'AMEUBLEMENT

APLICACION
TAPICERIA

PHYSICAL AND COLOUR FASTNESS CHARACTERISTICS

PHYSIQUE ET LES CARACTERISTIQUES DE SOLIDITE DES COULEURS

CARACTERÍSTICAS FÍSICAS Y DE SOLIDEZ DEL COLOR

Dry rubbing Frottement sec Frotamiento seco	500 Cycles Cycles Ciclos	UNI EN ISO 11640	>4 Grey scale Échelle de gris Escala de Grises
Wet rubbing Mouiller à friction Frotamiento mojado	150 Cycles Cycles Ciclos	UNI EN ISO 11640	4 Grey scale Échelle de gris Escala de Grises
Flexing endurance Flexion des eundurance Resistencia flexion	30.000 Cycles Cycles Ciclos	UNI EN ISO 5402	No surface damage or cracks Aucun dommage superficiel ou fissure Sin daños en la superficie o grietas
Colour fastness to light Solidité des teintures à la lumière Solidez del color a la luz		UNI EN ISO 105-B02	>4 Blue scale Échelle de bleu Escala de Azu
Tear resistance Résistance de larme Resistencia al desgorro		UNI EN ISO 3377-1	> 30 Newton
Fire Resistance Résistance au feu Resistencia al fuego		UNI EN 1021/1 UNI EN 1021/2	BS5852 Source Fuente 0.1



LEATHER CARE INSTRUCTIONS CLASSIC COLLECTION

Protect against excessive sunlight, dryness and heat:

Sunlight will fade and dry out the leather.

Dryness will cause the leather to crack.

Heat will dry out the leather and cause further damage.

How to remove spots and stains:

Blot excess liquid up as quickly as possible with a clean microfibre cloth.

If necessary, use clean lukewarm water only and let dry naturally. Do not dry with hair dryer, etc.

If water is used, clean the entire area where spot occurred seat cushion, arm, etc.

DO NOT RUB.

How to remove butter, oil or grease:

Wipe excess butter, oil or grease off the leather with a clean microfibre cloth. Then leave it alone as the spot should dissipate as much as possible into the leather in a short period of time.

Do not apply water or try to wash the butter, oil or grease spot.

How to remove chewing gum:

Place ice cubes in a plastic bag and apply on the chewing gum. Wait several minutes, lift the ice bag and remove the chewing gum.

General Care

DO NOT USE CHEMICALS, SADDLE SOAP, CLEANING SOLVENTS, FURNITURE POLISH, OILS, VARNISH, ABRASIVE CLEANNERS, SOAP OR AMMONIA WATER.


For futher informations, contact AMS.

These are recommended or suggested methods of cleaning. The manufacturer is not responsible for damage incurred while cleaning. Always try the cleaning method in a hidden area first to see results.




PRODUCT FEATURES AND IMPERFECTIONS THAT MAY OCCUR


IRON BRANDING




Hot and freeze branding is a technique for marking cattle to help identify the owner. However this is a decline technique because the alternatives, such as ear tags and even microchip collars are on the rise.



NECK CREASES



Neck creases are a normal phenomenon and do not affect the value of the leather. Neck wrinkles naturally occur in a hide as a result of the neck stretching and contracting.




Note: Although every effort is made to ensure that the leather ordered match the colours from our catalogues, slight variations may occur from batch. We advise to always make an sample request from the colour you may need.



PRODUCT FEATURES AND IMPERFECTIONS THAT MAY OCCUR


REGULAR GRAIN



Bovine of european origin, lightly buffed natural grain.



MEASURES



The average size of a hide in Pacific collection is 5.00 M2.

A - 1.70 MT (+-)

B - 2.15 MT (+-)

C - 1.95 MT (+-)

Note: Although every effort is made to ensure that the leather ordered match the colours from our catalogues, slight variations may occur from batch. We advise to always make an sample request from the colour you may need.