

FEATURES  
GUIDE

TUSCANIA  
COLLECTION





# DATA SHEET TUSCANIA COLLECTION

Pelle bovina mezzo fiore anilina a grana naturale di spessore finito 0,8 - 1,0 mm.  
 Concia al cromo. Superficie media pelle circa 4,8 - 5,0 mm<sup>2</sup>.  
 Tintura passante; rifinitura all' acqua trattata con resine, aniline e cere. Articolo con mano puntante, tatto scivoloso e aspetto semilucido.

Bovine of European origin, lightly buffed natural grain.  
 Finished thickness 0.8 - 1.0 mm. Average leather surface 4.8 - 5.0 sqm.  
 Chrome tannage. Aniline dyed finished with waxes for a distressed appearance. Natural unprotected surface.  
 Article with an uneven, slippery feel and semi-gloss appearance.

Europäisches Rindsleder, Typ Anilinleder.  
 Stärke 0,8 - 1,0 mm. Durchschnittliche Hautgröße ca. 4,8 - 5,0 qm.  
 Antikoptik, durch Behandlung mit Harzen und Wachsen.

Vachette origine européenne, pleine fleur, grains naturels.  
 Epaisseur: 0,8 - 1,0 mm. Superficie moyenne : 4,8 - 5,0 mm<sup>2</sup>.  
 Tannée au sel de chrome. Finition aniline teintée dans la masse avec une émulsion de ciré. Aspect semi brillant avec un effet vieilli.

Analisi Test Analysen Essai	Metodo di prova Test Method Prüfverfahren Test Méthode	Unità di misura Measurement Unit Maßeinheit Unité de Mesure	Garantito Guaranteed Garantiert Assuré
Resistenza allo sfregamento tipo Veslic Colour fastness to and fro rubbing Abriebfestigkeit nach Veslic	UNI EN ISO 11640	ISO 105 A03	> = 3 > = 3
Sudore Alcalino Sweat Alkaline Solution Alkalischer Schweiß Sueur Alcaline ISO 11641 pH 8	Secco - Dry - Trocken - A sec 50 c Umido - Wet - Nass - Humide 20 c  Sudore - Sweat - Schweiß - Sueur 20 c		> = 2
Resistenza alla luce, lampada ad arco di Xeno Colour fastness to artificial light Xenon arc UV-Beständigkeit, Xenon ARC-Labortest Résistance à la lumière, lampe Xénon	UNI EN ISO 105 B02	Scala dei Blu Blue Scale Blauskala Echelle des bleus	> = 2/3
Resistenza alla flessione Flexing endurance Biegefestigkeit Résistance à la flexion	ISO 5402	Cicli Cycles Zyklen Cycles	> 50.000
Determinazione del pH Determination of pH Bestimmung vom pH-Wert Evaluation du pH	ISO 4045	pH	> = 3,5
Indice di differenza (Solo per pH < 4) Difference figure (only for pH<4) Differenzindex (nur für pH < 4) Indice de différence (seulement pour le pH > 4)			> = 0,7
Resistenza allo Strappo Pantaloni Tear strength - Single edge tear Reißfestigkeit Hose Résistance au déchirement	ISO 3377-1	N	> = 20



# LEATHER CARE INSTRUCTIONS CLASSIC COLLECTION

## **Protect against excessive sunlight, dryness and heat:**

Sunlight will fade and dry out the leather.

Dryness will cause the leather to crack.

Heat will dry out the leather and cause further damage.

## **How to remove spots and stains:**

Blot excess liquid up as quickly as possible with a clean microfibre cloth.

If necessary, use clean lukewarm water only and let dry naturally. Do not dry with hair dryer, etc.

If water is used, clean the entire area where spot occurred seat cushion, arm, etc.

## **DO NOT RUB.**

## **How to remove butter, oil or grease:**

Wipe excess butter, oil or grease off the leather with a clean microfibre cloth. Then leave it alone as the spot should dissipate as much as possible into the leather in a short period of time.

**Do not apply** water or try to wash the butter, oil or grease spot.

## **How to remove chewing gum:**

Place ice cubes in a plastic bag and apply on the chewing gum. Wait several minutes, lift the ice bag and remove the chewing gum.

## **General Care**

**DO NOT USE CHEMICALS, SADDLE SOAP, CLEANING SOLVENTS, FURNITURE POLISH, OILS, VARNISH, ABRASIVE CLEANERS, SOAP OR AMMONIA WATER.**


**For further informations, contact AMS.**

These are recommended or suggested methods of cleaning. The manufacturer is not responsible for damage incurred while cleaning. Always try the cleaning method in a hidden area first to see results.



## PRODUCT FEATURES AND IMPERFECTIONS THAT MAY OCCUR


### NECK CREASES



Neck creases are a normal phenomenon and do not affect the value of the leather. Neck wrinkles naturally occur in a hide as a result of the neck stretching and contracting.



### NATURAL GRAIN



Bovine of European origin, with a distressed vintage effect.



Note: Although every effort is made to ensure that the leather ordered match the colours from our catalogues, slight variations may occur from batch. We advise to always make an sample request from the colour you may need.



## PRODUCT FEATURES AND IMPERFECTIONS THAT MAY OCCUR

### MEASURES



The average size of a hide in Tuscania collection is 5.00 M2.

A - 1.70 MT (+-)

B - 2.15 MT (+-)

C - 1.95 MT (+-)

Note: Although every effort is made to ensure that the leather ordered match the colours from our catalogues, slight variations may occur from batch. We advise to always make an sample request from the colour you may need.